



ROLLER



PANEL



ROMAN

Technical Data

Composition	100% polyester
Width	3,000mm
Weight	Blockout 430gsm Light filtering 260gsm
Thickness	Blockout 0.70mm +/-5% Light filtering 0.60mm +/-5%
Opacity/Openness	Blockout tested to AS-2663-1999
Light Fastness	≥ 7 (Blue wool scale)
Coating	Blockout coated with acrylic foam Light Filtering stiffened with acrylic
Flame Retardant	Product is designed and manufactured to comply with Building Code of Australia requirements for class 2 to 9 buildings
Cleaning	Surface dust can be removed with vacuum or a soft cloth



MADE IN AUSTRALIA



5 YEAR WARRANTY



BLOCKOUT



LIGHT FILTERING



PVC FREE

Solar Properties

	European standard tested to DIN EN 410: 2011								Tested to EN 14501	
	Ts	Rs	As	Tv/ Vlt	Tuv	O-F	G-value	Single Glass Reference Glazing A [g window 0.85] [U window 5.7] g-total	High Performance Glass Reference Glazing D [g window 0.32] [U window 1.1] g-total	
Owl LF	33	50	17	27	19	0.5	0.37	0.47	0.27	
Eland LF	28	47	25	19	10	0.5	0.34	0.48	0.27	
Jackal LF	23	41	36	11	7	0.5	0.32	0.50	0.27	
Albatross LF	31	52	17	28	15	0.5	0.35	0.45	0.26	
Antelope LF	9	24	67	3	2	0.5	0.25	0.58	0.29	
Hydrax LF	23	43	34	13	9	0.5	0.31	0.49	0.27	
Caribou LF	20	38	42	6	4	0.5	0.31	0.52	0.28	
Jackal BO	0	73	27	0	0	0.5	0.06	0.29	0.24	

Ts Solar Transmittance **As** Solar Absorbance **G-Value** % Solar Radiation through Fabric
Rs Solar Reflection **Tv** Visual Light Transmission **G-Total** % Solar Radiation through Blind and Window

